



PHYSICAL PROPERTY DATA SHEET

PEBBLE TOP COMPOUNDS – VARIOUS COLORS

<u>Property</u>	<u>Result</u>	<u>ASTM</u>
Hardness – 10 Sec. Delay	80A	D2240
Tensile Strength	2600 PSI	D412
Ultimate Elongation	360 %	D412
Graves Tear	260 PPI	D1004
100% Modulus	1360 PSI	D412
Brittleness Temperature	-33° F / 38° C	D746
UV Resistance	Yes	
Spec. Gravity	1.24	D792

The information contained herein is believed to be reliable but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small scale equipment and does not necessarily indicate end product performance. Full scale testing and product performance are the responsibility of the user. The Wimplex→ Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material. SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.